



UN38.3 测试报告

UN38.3 Test Report

样品名称:	可充电锂离子电池 BC25R
Sample Name:	Rechargeable Li-ion Battery BC25R
型号规格:	BC25R 3.6V 2600mAh 9.36Wh
Model:	
委托单位:	深圳市朗恒电子有限公司
Applicant:	SHEN ZHEN LANG HENG ELECTRONIC CO.,LTD
检验项目:	高度模拟、温度试验、振动、冲击、外部短路、撞击、过度充电、强制放电
Test Items:	Altitude simulation, Thermal test, Vibration, Shock, External short circuit, Impact, Overcharge, Forced discharge
检验类别:	委托检验
Test Category:	Commission test

北京迪捷姆空运技术开发有限公司

Beijing DGM Air Transport Technology Co., Ltd.

报告书使用约定

Terms of the Using of the Report

1. 本公司依据委托人（托运人或其代理人）提供的物品，做出测试并出具此报告书。
The report is issued by DGM China according to the test of the goods and the information of its shipping provided by the applicant (shipper or his agent).
2. 依据测试的需要，本公司要求委托人提供真实、完整的货物样品及资料。
According to the demand of test, DGM China requires the applicant to provide true and exact sample and data of the cargo.
3. 委托人保证申报的物品和/或提供的样品与交运的货物是一致的。
The applicant guarantees that the declared goods and/or the sample who provides should be identical with the contents of cargo that is to be transported.
4. 本公司仅对样品的测试结果负责。
DGM China is only responsible for the test of the sample provided by the applicant.
5. 本报告书经主检员、审核人和批准人签字并加盖本公司印章后生效。
This report will be effective only after it is signed by the inspector, checker and approver, and stamped by DGM China.
6. 未经本公司书面批准，不得复制本报告书。
The duplicating of this report is prohibited without the written approval of DGM China.
7. 私自转让、复制、盗用、冒用、涂改、或以任何媒体形式篡改的报告书无效。
The report is invalid when anything of the following happens - illegal transfer, reproduce, embezzlement, imposture, modification or tampering in any media form.

地址:	北京首都机场货运北路天竺综合保税区 BGS 货运楼 249 室	邮编:	
Address:	room 249, BGS cargo Terminal, Cargo Road, Capital international airport, Beijing, China	Postcode:	101300
电话:	010-69479673	传真:	010-69479621
Tel:		Fax:	
网址:	www.dgmchina.com.cn	邮箱:	test@dgmchina.com.cn
Website:		E-mail:	

北京迪捷姆空运技术开发有限公司
Beijing DGM Air Transport Technology Co., Ltd.
UN38.3 测试报告
UN38.3 Test Report

样品名称 Sample Name	可充电锂离子电池 BC25R Rechargeable Li-ion Battery BC25R		商标 Trademark	FENIX
			型号/规格 Model	BC25R 3.6V 2600mAh 9.36Wh
委托单位 Applicant	名称 Name	深圳市朗恒电子有限公司 SHEN ZHEN LANG HENG ELECTRONIC CO.,LTD		
	地址 Address	深圳市宝安 33 区东方明工业城二栋八楼 8/F, 2nd Building, DongFangMing Industrial Center, 33rd District, Bao'an, Shenzhen		
来样方式 Means of Receiving	委托方送样 Submitted by applicant		送样日期 Accepted Date	2018.05.22
检验日期 Test Date	2018.06.01-2018.07.04			
检验地点 Test Site	本检测室（电池室） DGM(Battery room)			
检验项目 Test Items	高度模拟、温度试验、振动、冲击、外部短路、撞击、过度充电、强制放电 Altitude simulation, Thermal test, Vibration, Shock, External short circuit, Impact, Overcharge, Forced discharge			
检验依据 Test Method	联合国《关于危险货物运输的建议书-试验和标准手册》（第 6 版修订一）38.3 节 UN Recommendations on the Transport of Dangerous Goods Manual of Tests and Criteria ST/SG/AC.10/11/Rev.6 Amendment 1/ Subsection 38.3			
检验结论 Conclusion	<p>根据联合国《关于危险货物运输的建议书-试验和标准手册》（第 6 版修订一）38.3 节的规定，该电池样品通过所有项目检测，符合该条款的性能要求。</p> <p>The samples have passed all test items of UN Recommendations on the Transport of Dangerous Goods - Manual of Tests and Criteria ST/SG/AC.10/11/Rev.6 Amendment 1/ Subsection 38.3.</p> <p>检验单位(盖章) Test Lab(Stamp)</p> <p>签发日期(Issue Date): 2018 年 07 月 10 日</p>			

检测:

Tested by:

罗晓峰

审核:

Checked by:

宋明

批准:

Approved by:

冯海

电芯信息 Information for cell			
电芯生产厂家 Cell manufacturer	常德毅力能源有限公司 CHANGDE YIKLIK ENERGY CO.,LTD		
电芯厂家联系电话 Phone number	//	邮箱 e-mail	//
电芯厂家地址 Address	湖南省安乡县深柳镇洞庭大道南段长岭洲村（工业园内） Southern Dongting Avenue, Changlingzhou Village, Shenliu Town, Anxiang Country, Hunan Province, P.R, China(Inside Industrial Park)		
电芯厂家网址 Website	//		
Pack 厂家 Pack manufacturer	深圳市优能电源技术有限公司 SHENZHEN YOUR POWER TECHNOLOGY CO.,LTD		
Pack 厂家联系电话 Phone number	/	邮箱 e-mail	//
Pack 厂家地址 Address	深圳市龙华区观澜街道盛德兰工业园办公楼 4 楼 4/F, Office Building SDL Industry Park, Longhua District, Shenzhen, China		
Pack 厂家网址 Website	//		

电芯信息 Information for cell			
标称电压 Nominal Voltage	3.7V	额定容量 Rated Capacity	2600mAh
最大连续充电电流 Maximum charging current	1300mA	最大放电电流 Maximum discharge current	2600mA
充电限制电压 Limited charging voltage	4.2V	放电截止电压 Cut-Off voltage	3.0V
外观形状 Appearance	蓝色圆柱体 Blue cylinder	电芯尺寸 Cell size	Φ18.4×66.3mm

北京迪捷姆空运技术开发有限公司
 Beijing DGM Air Transport Technology Co., Ltd.
UN38.3 测试报告
UN38.3 Test Report

序号 No.	检验项目 Test Items	标准要求或标准条款 Standard Requirement or the Clause of Standard	检验结果 Test Result	单项评价 Conclusion	备注 Remark
1	高度模拟 Altitude Simulation	ST/SG/AC.10/11/Rev.6 Amendment 1/ Subsection 38.3 Test T.1	无泄漏、无排气、无解体、无破裂、无起火， 试验后的开路电压不低于试验前的 90%。 No leakage, no venting, no disassembly, no rupture and no fire. The open circuit voltage of each battery after testing is not less than 90% of its voltage immediately prior to this procedure.	符合 Pass	/
2	温度试验 Thermal Test	ST/SG/AC.10/11/Rev.6 Amendment 1/ Subsection 38.3 Test T.2	无泄漏、无排气、无解体、无破裂、无起火， 试验后的开路电压不低于试验前的 90%。 No leakage, no venting, no disassembly, no rupture and no fire. The open circuit voltage of each battery after testing is not less than 90% of its voltage immediately prior to this procedure.	符合 Pass	/
3	振动 Vibration	ST/SG/AC.10/11/Rev.6 Amendment 1/ Subsection 38.3 Test T.3	无泄漏、无排气、无解体、无破裂、无起火， 试验后的开路电压不低于试验前的 90%。 No leakage, no venting, no disassembly, no rupture and no fire. The open circuit voltage of each battery after testing is not less than 90% of its voltage immediately prior to this procedure.	符合 Pass	/
4	冲击 Shock	ST/SG/AC.10/11/Rev.6 Amendment 1/ Subsection 38.3 Test T.4	无泄漏、无排气、无解体、无破裂、无起火， 试验后的开路电压不低于试验前的 90%。 No leakage, no venting, no disassembly, no rupture and no fire. The open circuit voltage of each battery after testing is not less than 90% of its voltage immediately prior to this procedure.	符合 Pass	/
5	外部短路 External Short Circuit	ST/SG/AC.10/11/Rev.6 Amendment 1/ Subsection 38.3 Test T.5	外壳温度不超过 170 °C，无解体、无破裂、无 起火。 External temperature does not exceed 170°C. No disassembly, no rupture and no fire.	符合 Pass	/
6	撞击 Impact	ST/SG/AC.10/11/Rev.6 Amendment 1/ Subsection 38.3 Test T.6	外壳温度不超过 170 °C，无解体、无起火。 External temperature does not exceed 170°C. No disassembly, no fire.	符合 Pass	/
7	过度充电 Overcharge	ST/SG/AC.10/11/Rev.6 Amendment 1/ Subsection 38.3 Test T.7	无解体、无起火。 No disassembly, no fire.	符合 Pass	/
8	强制放电 Forced Discharge	ST/SG/AC.10/11/Rev.6 Amendment 1/ Subsection 38.3 Test T.8	无解体、无起火。 No disassembly, no fire.	符合 Pass	/
以下空白 Blank below					

T.1: 高度模拟

T.1: Altitude Simulation

样品编号 Sample No.	样品状态 Sample Status	测试前 Pre-test		测试后 After-test				有无泄漏、排气、解体、破裂、起火 Leakage, Venting, Disassembly, Rupture, Fire(Yes/No)
		质量 Mass	开路电压 OCV	质量 Mass	质量损失 Mass Loss	开路电压 OCV	剩余电压 Residual	
		$m_1(g)$	$V_1(V)$	$m_2(g)$	(%)	$V_2(V)$	OCV (%)	
A1	首次完全充电 First cycle fully charged	47.313	4.165	47.308	0.011	4.162	99.93	No
A2	首次完全充电 First cycle fully charged	47.010	4.163	47.005	0.011	4.161	99.95	No
A3	首次完全充电 First cycle fully charged	47.473	4.165	47.467	0.013	4.163	99.95	No
A4	首次完全充电 First cycle fully charged	47.141	4.163	47.136	0.011	4.160	99.93	No
A5	首次完全充电 First cycle fully charged	47.230	4.161	47.224	0.013	4.159	99.95	No
A6	25 次完全充电 25 cycles fully charged	47.066	4.164	47.061	0.011	4.162	99.95	No
A7	25 次完全充电 25 cycles fully charged	47.258	4.162	47.255	0.006	4.160	99.95	No
A8	25 次完全充电 25 cycles fully charged	46.594	4.163	46.588	0.013	4.161	99.95	No
A9	25 次完全充电 25 cycles fully charged	46.976	4.161	46.971	0.011	4.159	99.95	No
A10	25 次完全充电 25 cycles fully charged	47.461	4.165	47.456	0.011	4.162	99.93	No

以下空白

Blank below

T.2: 温度试验

T.2: Thermal Test

样品编号 Sample No.	样品状态 Sample Status	测试前 Pre-test		测试后 After-test				有无泄漏、排气、 解体、破裂、起火 Leakage, Venting, Disassembly, Rupture, Fire(Yes/No)
		质量 Mass	开路电压 OCV	质量 Mass	质量损失 Mass Loss	开路电压 OCV	剩余电压 Residual	
		m ₁ (g)	V ₁ (V)	m ₂ (g)	(%)	V ₂ (V)	OCV (%)	
A1	首次完全充电 First cycle fully charged	47.308	4.162	47.282	0.055	4.086	98.17	No
A2	首次完全充电 First cycle fully charged	47.005	4.161	46.977	0.060	4.085	98.17	No
A3	首次完全充电 First cycle fully charged	47.467	4.163	47.438	0.061	4.088	98.20	No
A4	首次完全充电 First cycle fully charged	47.136	4.160	47.106	0.064	4.083	98.15	No
A5	首次完全充电 First cycle fully charged	47.224	4.159	47.199	0.053	4.087	98.27	No
A6	25 次完全充电 25 cycles fully charged	47.061	4.162	47.034	0.057	4.099	98.49	No
A7	25 次完全充电 25 cycles fully charged	47.255	4.160	47.231	0.051	4.093	98.39	No
A8	25 次完全充电 25 cycles fully charged	46.588	4.161	46.560	0.060	4.094	98.39	No
A9	25 次完全充电 25 cycles fully charged	46.971	4.159	46.948	0.049	4.094	98.44	No
A10	25 次完全充电 25 cycles fully charged	47.456	4.162	47.432	0.051	4.098	98.46	No
以下空白 Blank below								

T.3: 振动

T.3: Vibration

样品编号 Sample No.	样品状态 Sample Status	测试前 Pre-test		测试后 After-test				有无泄漏、排气、 解体、破裂、起火 Leakage, Venting, Disassembly, Rupture, Fire(Yes/No)
		质量 Mass	开路电压 OCV	质量 Mass	质量损失 Mass Loss	开路电压 OCV	剩余电压 Residual	
		$m_1(\text{g})$	$V_1(\text{V})$	$m_2(\text{g})$	(%)	$V_2(\text{V})$	OCV (%)	
A1	首次完全充电 First cycle fully charged	47.282	4.086	47.266	0.034	4.082	99.90	No
A2	首次完全充电 First cycle fully charged	46.977	4.085	46.959	0.038	4.083	99.95	No
A3	首次完全充电 First cycle fully charged	47.438	4.088	47.422	0.034	4.086	99.95	No
A4	首次完全充电 First cycle fully charged	47.106	4.083	47.087	0.040	4.080	99.93	No
A5	首次完全充电 First cycle fully charged	47.199	4.087	47.181	0.038	4.084	99.93	No
A6	25 次完全充电 25 cycles fully charged	47.034	4.099	47.019	0.032	4.095	99.90	No
A7	25 次完全充电 25 cycles fully charged	47.231	4.093	47.214	0.036	4.091	99.95	No
A8	25 次完全充电 25 cycles fully charged	46.560	4.094	46.546	0.030	4.092	99.95	No
A9	25 次完全充电 25 cycles fully charged	46.948	4.094	46.931	0.036	4.092	99.95	No
A10	25 次完全充电 25 cycles fully charged	47.432	4.098	47.412	0.034	4.095	99.93	No

以下空白
Blank below

T.4: 冲击

T.4: Shock

样品编号 Sample No.	样品状态 Sample Status	测试前 Pre-test		测试后 After-test				有无泄漏、排气、 解体、破裂、起火 Leakage, Venting, Disassembly, Rupture, Fire(Yes/No)
		质量 Mass $m_1(g)$	开路电压 OCV $V_1(V)$	质量 Mass $m_2(g)$	质量损失 Mass Loss (%)	开路电压 OCV $V_2(V)$	剩余电压 Residual OCV (%)	
A1	首次完全充电 First cycle fully charged	47.266	4.082	47.252	0.030	4.080	99.95	No
A2	首次完全充电 First cycle fully charged	46.959	4.083	46.941	0.038	4.081	99.95	No
A3	首次完全充电 First cycle fully charged	47.422	4.086	47.407	0.032	4.083	99.93	No
A4	首次完全充电 First cycle fully charged	47.087	4.080	47.072	0.032	4.077	99.93	No
A5	首次完全充电 First cycle fully charged	47.181	4.084	47.168	0.028	4.082	99.95	No
A6	25 次完全充电 25 cycles fully charged	47.019	4.095	47.005	0.030	4.092	99.93	No
A7	25 次完全充电 25 cycles fully charged	47.214	4.091	47.203	0.023	4.088	99.93	No
A8	25 次完全充电 25 cycles fully charged	46.546	4.092	46.533	0.028	4.089	99.93	No
A9	25 次完全充电 25 cycles fully charged	46.931	4.092	46.915	0.034	4.090	99.95	No
A10	25 次完全充电 25 cycles fully charged	47.412	4.095	47.399	0.011	4.093	99.95	No
以下空白 Blank below								

T.5: 外部短路**T.5: External Short Circuit**

样品编号 Sample No	样品状态 Sample Status	样品表面最高温度(°C) Highest External Temperature/°C	有无解体、破裂、起火 Disassembly, Rupture, Fire(Yes/No)
A1	首次完全充电 First cycle fully charged	59.7	No
A2	首次完全充电 First cycle fully charged	60.1	No
A3	首次完全充电 First cycle fully charged	59.5	No
A4	首次完全充电 First cycle fully charged	58.3	No
A5	首次完全充电 First cycle fully charged	59.1	No
A6	25次完全充电 25 cycles fully charged	60.0	No
A7	25次完全充电 25 cycles fully charged	60.4	No
A8	25次完全充电 25 cycles fully charged	59.2	No
A9	25次完全充电 25 cycles fully charged	60.2	No
A10	25次完全充电 25 cycles fully charged	59.8	No
以下空白 Blank below			

T.6: 撞击**T.6: Impact**

样品编号 Sample No.	样品状态 Sample Status	样品表面最高温度(℃) Highest External Temperature/℃	有无解体、起火 Disassembly, Fire(Yes/No)
B1	首次 50%容量 First cycle charged 50% rated capacity	133.5	No
B2	首次 50%容量 First cycle charged 50% rated capacity	136.2	No
B3	首次 50%容量 First cycle charged 50% rated capacity	135.9	No
B4	首次 50%容量 First cycle charged 50% rated capacity	130.8	No
B5	首次 50%容量 First cycle charged 50% rated capacity	150.5	No
B6	25 次 50%容量 25 cycles charged 50% rated capacity	142.6	No
B7	25 次 50%容量 25 cycles charged 50% rated capacity	139.4	No
B8	25 次 50%容量 25 cycles charged 50% rated capacity	145.0	No
B9	25 次 50%容量 25 cycles charged 50% rated capacity	138.7	No
B10	25 次 50%容量 25 cycles charged 50% rated capacity	140.6	No
以下空白 Blank below			

T.7: 过度充电

T.7: Overcharge

样品编号 Sample No.	样品状态 Sample Status	有无解体、起火 Disassembly, Fire(Yes/No)
C1	首次完全充电 First cycle fully charged	No
C2	首次完全充电 First cycle fully charged	No
C3	首次完全充电 First cycle fully charged	No
C4	首次完全充电 First cycle fully charged	No
C5	25次完全充电 25 cycles fully charged	No
C6	25次完全充电 25 cycles fully charged	No
C7	25次完全充电 25 cycles fully charged	No
C8	25次完全充电 25 cycles fully charged	No

以下空白

Blank below

T.8: 强制放电

T.8: Forced Discharge

样品编号 Sample No.	样品状态 Sample Status	有无解体、起火 Disassembly, Fire(Yes/No)
D1	首次完全放电 First cycle fully discharged	No
D2	首次完全放电 First cycle fully discharged	No
D3	首次完全放电 First cycle fully discharged	No
D4	首次完全放电 First cycle fully discharged	No
D5	首次完全放电 First cycle fully discharged	No
D6	首次完全放电 First cycle fully discharged	No
D7	首次完全放电 First cycle fully discharged	No
D8	首次完全放电 First cycle fully discharged	No
D9	首次完全放电 First cycle fully discharged	No
D10	首次完全放电 First cycle fully discharged	No
D11	25次完全放电 25 cycles fully discharged	No
D12	25次完全放电 25 cycles fully discharged	No
D13	25次完全放电 25 cycles fully discharged	No
D14	25次完全放电 25 cycles fully discharged	No
D15	25次完全放电 25 cycles fully discharged	No
D16	25次完全放电 25 cycles fully discharged	No
D17	25次完全放电 25 cycles fully discharged	No
D18	25次完全放电 25 cycles fully discharged	No
D19	25次完全放电 25 cycles fully discharged	No
D20	25次完全放电 25 cycles fully discharged	No
以下空白 Blank below		


UN38.3 测试报告

UN38.3 Test Report

电芯照片/Cell pictures



保护装置/Protective devices



* End of the report *