



UN38.3 测试报告

UN38.3 Test Report

样品名称:	可充电锂离子电池 ARB-L18-2600U
Sample Name:	Rechargeable Li-ion Battery ARB-L18-2600U
型号规格:	ARB-L18-2600U 3.6V 2600mAh 9.36Wh
Model:	
委托单位:	深圳市朗恒电子有限公司
Applicant:	SHEN ZHEN LANG HENG ELECTRONIC CO.,LTD
检验项目:	高度模拟、温度试验、振动、冲击、外部短路、撞击、过度充电、强制放电
Test Items:	Altitude simulation, Thermal test, Vibration, Shock, External short circuit, Impact, Overcharge, Forced discharge
检验类别:	委托检验
Test Category:	Commission test

北京迪捷姆空运技术开发有限公司

Beijing DGM Air Transport Technology Co., Ltd.

报告书使用约定

Terms of the Using of the Report

1. 本公司依据委托人（托运人或其代理人）提供的物品，做出测试并出具此报告书。
The report is issued by DGM China according to the test of the goods and the information of its shipping provided by the applicant (shipper or his agent).
2. 依据测试的需要，本公司要求委托人提供真实、完整的货物样品及资料。
According to the demand of test, DGM China requires the applicant to provide true and exact sample and data of the cargo.
3. 委托人保证申报的物品和/或提供的样品与交运的货物是一致的。
The applicant guarantees that the declared goods and/or the sample who provides should be identical with the contents of cargo that is to be transported.
4. 本公司仅对样品的测试结果负责。
DGM China is only responsible for the test of the sample provided by the applicant.
5. 本报告书经主检员、审核人和批准人签字并加盖本公司印章后生效。
This report will be effective only after it is signed by the inspector, checker and approver, and stamped by DGM China.
6. 未经本公司书面批准，不得复制本报告书。
The duplicating of this report is prohibited without the written approval of DGM China.
7. 私自转让、复制、盗用、冒用、涂改、或以任何媒体形式篡改的报告书无效。
The report is invalid when anything of the following happens - illegal transfer, reproduce, embezzlement, imposture, modification or tampering in any media form.

地址：北京首都机场货运北路天竺综合保税区 BGS 货运楼 249 室 邮编：

Address: room 249, BGS cargo Terminal, Cargo Road, Capital international airport, Beijing, China Postcode: 101300

电话：010-69479673

Tel:

传真：010-69479621

Fax:

网址：www.dgmchina.com.cn

Website:

邮箱：test@dgmchina.com.cn

E-mail:

北京迪捷姆空运技术开发有限公司
Beijing DGM Air Transport Technology Co., Ltd.
UN38.3 测试报告
UN38.3 Test Report

样品名称 Sample Name	可充电锂离子电池 ARB-L18-2600U Rechargeable Li-ion Battery ARB-L18-2600U		商标 Trademark	FENIX
			型号/规格 Model	ARB-L18-2600U 3.6V 2600mAh 9.36Wh
委托单位 Applicant	名称 Name	深圳市朗恒电子有限公司 SHEN ZHEN LANG HENG ELECTRONIC CO.,LTD		
	地址 Address	深圳市宝安 33 区东方明工业城二栋八楼 8/F, 2nd Building, DongFangMing Industrial Center, 33rd District, Bao'an, Shenzhen		
来样方式 Means of Receiving	委托方送样 Submitted by applicant		送样日期 Accepted Date	2018.09.16
检验日期 Test Date	2018.09.17-2018.10.24			
检验地点 Test Site	本检测室（电池室） DGM(Battery room)			
检验项目 Test Items	高度模拟、温度试验、振动、冲击、外部短路、撞击、过度充电、强制放电 Altitude simulation, Thermal test, Vibration, Shock, External short circuit, Impact, Overcharge, Forced discharge			
检验依据 Test Method	联合国《关于危险货物运输的建议书-试验和标准手册》（第 6 版修订一）38.3 节 UN Recommendations on the Transport of Dangerous Goods Manual of Tests and Criteria ST/SG/AC.10/11/Rev.6 Amendment 1/ Subsection 38.3			
检验结论 Conclusion	<p>根据联合国《关于危险货物运输的建议书-试验和标准手册》（第 6 版修订一）38.3 节的规定，该电池样品通过所有项目检测，符合该条款的性能要求。</p> <p>The samples have passed all test items of UN Recommendations on the Transport of Dangerous Goods - Manual of Tests and Criteria ST/SG/AC.10/11/Rev.6 Amendment 1/ Subsection 38.3.</p> <p>检验单位(盖章) Test Lab(Stamp)</p> <p>签发日期(Issue Date): 2018 年 10 月 31 日</p>			

检测:

Tested by:

罗晓峰

审核:

Checked by:

宋明

批准:

Approved by:

冯海

电池信息 Information for battery			
电芯生产厂家 Cell manufacturer	郑州比克电池有限公司 ZHENGZHOU BAK BATTERY CO.,LTD		
电芯厂家联系电话 Phone number	+86-0371-62033103	邮箱 e-mail	Sales@bak.com.cn
电芯厂家地址 Address	河南省郑州是中牟县郑庵镇刘巧村 Liuqiao Village Zhengan town Zhongmou country Zhengzhou, Henan China		
电芯厂家网址 Website	//		
Pack 厂家 Pack manufacturer	深圳市优能电源技术有限公司 SHENZHEN YOUR POWER TECHNOLOGY CO.,LTD		
Pack 厂家联系电话 Phone number	13603018105	邮箱 e-mail	Sales@yourpower.cn
Pack 厂家地址 Address	深圳市龙华区观澜街道盛德兰工业园办公楼 4 楼 4/F, Office Building SDL Industry Park, Longhua District, Shenzhen, China		
Pack 厂家网址 Website	//		

电芯信息 Information for cell			
电芯型号 Cell model	H18650CIL		
标称电压 Nominal Voltage	3.6V	额定容量 Rated Capacity	2600mAh
最大连续充电电流 Maximum charging current	1300mA	最大放电电流 Maximum discharge current	2600mA
充电限制电压 Limited charging voltage	4.2V	放电截止电压 Cut-Off voltage	2.75V
外观形状 Appearance	灰色圆柱体 Gray cylinder	电芯尺寸 Cell size	Φ18.3×65.0mm

电池信息 Information for battery			
最大连续充电电流 Maximum charging current	1300mA	最大放电电流 Maximum discharge current	2600mA
充电限制电压 Limited charging voltage	4.2V	放电截止电压 Cut-Off voltage	2.75V
规格/型号 Model	ARB-L18-2600U 3.6V 2600mAh 9.36Wh	电池尺寸 Battery size	Φ18.4×70.5mm
组成电芯数量 Number of cell	单电芯 Single cell	外观形状 Appearance	红黑杂色圆柱体 Red-black cylinder

北京迪捷姆空运技术开发有限公司
Beijing DGM Air Transport Technology Co., Ltd.
UN38.3 测试报告
UN38.3 Test Report

序号 No.	检验项目 Test Items	标准要求或标准条款 Standard Requirement or the Clause of Standard	检验结果 Test Result	单项评价 Conclusion	备注 Remark
1	高度模拟 Altitude Simulation	ST/SG/AC.10/11/Rev.6 Amendment 1/ Subsection 38.3 Test T.1	无泄漏、无排气、无解体、无破裂、无起火， 试验后的开路电压不低于试验前的 90%。 No leakage, no venting, no disassembly, no rupture and no fire. The open circuit voltage of each battery after testing is not less than 90% of its voltage immediately prior to this procedure.	符合 Pass	/
2	温度试验 Thermal Test	ST/SG/AC.10/11/Rev.6 Amendment 1/ Subsection 38.3 Test T.2	无泄漏、无排气、无解体、无破裂、无起火， 试验后的开路电压不低于试验前的 90%。 No leakage, no venting, no disassembly, no rupture and no fire. The open circuit voltage of each battery after testing is not less than 90% of its voltage immediately prior to this procedure.	符合 Pass	/
3	振动 Vibration	ST/SG/AC.10/11/Rev.6 Amendment 1/ Subsection 38.3 Test T.3	无泄漏、无排气、无解体、无破裂、无起火， 试验后的开路电压不低于试验前的 90%。 No leakage, no venting, no disassembly, no rupture and no fire. The open circuit voltage of each battery after testing is not less than 90% of its voltage immediately prior to this procedure.	符合 Pass	/
4	冲击 Shock	ST/SG/AC.10/11/Rev.6 Amendment 1/ Subsection 38.3 Test T.4	无泄漏、无排气、无解体、无破裂、无起火， 试验后的开路电压不低于试验前的 90%。 No leakage, no venting, no disassembly, no rupture and no fire. The open circuit voltage of each battery after testing is not less than 90% of its voltage immediately prior to this procedure.	符合 Pass	/
5	外部短路 External Short Circuit	ST/SG/AC.10/11/Rev.6 Amendment 1/ Subsection 38.3 Test T.5	外壳温度不超过 170 °C，无解体、无破裂、无 起火。 External temperature does not exceed 170°C. No disassembly, no rupture and no fire.	符合 Pass	/
6	撞击 Impact	ST/SG/AC.10/11/Rev.6 Amendment 1/ Subsection 38.3 Test T.6	外壳温度不超过 170 °C，无解体、无起火。 External temperature does not exceed 170°C. No disassembly, no fire.	符合 Pass	/
7	过度充电 Overcharge	ST/SG/AC.10/11/Rev.6 Amendment 1/ Subsection 38.3 Test T.7	无解体、无起火。 No disassembly, no fire.	符合 Pass	/
8	强制放电 Forced Discharge	ST/SG/AC.10/11/Rev.6 Amendment 1/ Subsection 38.3 Test T.8	无解体、无起火。 No disassembly, no fire.	符合 Pass	/
以下空白 Blank below					

T.1: 高度模拟

T.1: Altitude Simulation

样品编号 Sample No.	样品状态 Sample Status	测试前 Pre-test		测试后 After-test				有无泄漏、排气、解体、破裂、起火 Leakage, Venting, Disassembly, Rupture, Fire(Yes/No)
		质量 Mass	开路电压 OCV	质量 Mass	质量损失 Mass Loss	开路电压 OCV	剩余电压 Residual	
		$m_1(g)$	$V_1(V)$	$m_2(g)$	(%)	$V_2(V)$	OCV (%)	
A1	首次完全充电 First cycle fully charged	49.226	4.173	49.220	0.012	4.169	99.90	No
A2	首次完全充电 First cycle fully charged	48.922	4.171	48.916	0.012	4.168	99.93	No
A3	首次完全充电 First cycle fully charged	49.210	4.170	49.206	0.008	4.168	99.95	No
A4	首次完全充电 First cycle fully charged	49.077	4.174	49.070	0.014	4.171	99.93	No
A5	首次完全充电 First cycle fully charged	49.244	4.171	49.240	0.008	4.167	99.90	No
A6	25 次完全充电 25 cycles fully charged	49.063	4.177	49.058	0.010	4.175	99.95	No
A7	25 次完全充电 25 cycles fully charged	48.914	4.180	48.909	0.010	4.178	99.95	No
A8	25 次完全充电 25 cycles fully charged	49.024	4.175	49.019	0.010	4.173	99.95	No
A9	25 次完全充电 25 cycles fully charged	49.299	4.179	49.294	0.010	4.177	99.95	No
A10	25 次完全充电 25 cycles fully charged	49.066	4.178	49.063	0.006	4.176	99.95	No

以下空白
Blank below

T.2: 温度试验

T.2: Thermal Test

样品编号 Sample No.	样品状态 Sample Status	测试前 Pre-test		测试后 After-test				有无泄漏、排气、 解体、破裂、起火 Leakage, Venting, Disassembly, Rupture, Fire(Yes/No)
		质量 Mass	开路电压 OCV	质量 Mass	质量损失 Mass Loss	开路电压 OCV	剩余电压 Residual	
		m ₁ (g)	V ₁ (V)	m ₂ (g)	(%)	V ₂ (V)	OCV (%)	
A1	首次完全充电 First cycle fully charged	49.220	4.169	49.206	0.028	4.135	99.18	No
A2	首次完全充电 First cycle fully charged	48.916	4.168	48.899	0.035	4.133	99.16	No
A3	首次完全充电 First cycle fully charged	49.206	4.168	49.193	0.026	4.132	99.14	No
A4	首次完全充电 First cycle fully charged	49.070	4.171	49.052	0.037	4.134	99.11	No
A5	首次完全充电 First cycle fully charged	49.240	4.167	49.227	0.026	4.133	99.18	No
A6	25 次完全充电 25 cycles fully charged	49.058	4.175	49.042	0.033	4.142	99.21	No
A7	25 次完全充电 25 cycles fully charged	48.909	4.178	48.893	0.033	4.143	99.16	No
A8	25 次完全充电 25 cycles fully charged	49.019	4.173	49.001	0.037	4.139	99.19	No
A9	25 次完全充电 25 cycles fully charged	49.294	4.177	49.282	0.024	4.141	99.14	No
A10	25 次完全充电 25 cycles fully charged	49.063	4.176	49.043	0.041	4.140	99.14	No
以下空白 Blank below								

T.3: 振动

T.3: Vibration

样品编号 Sample No.	样品状态 Sample Status	测试前 Pre-test		测试后 After-test				有无泄漏、排气、 解体、破裂、起火 Leakage, Venting, Disassembly, Rupture, Fire(Yes/No)
		质量 Mass m ₁ (g)	开路电压 OCV V ₁ (V)	质量 Mass m ₂ (g)	质量损失 Mass Loss (%)	开路电压 OCV V ₂ (V)	剩余电压 Residual OCV (%)	
A1	首次完全充电 First cycle fully charged	49.206	4.135	49.202	0.008	4.132	99.93	No
A2	首次完全充电 First cycle fully charged	48.899	4.133	48.894	0.010	4.131	99.95	No
A3	首次完全充电 First cycle fully charged	49.193	4.132	49.189	0.008	4.129	99.93	No
A4	首次完全充电 First cycle fully charged	49.052	4.134	49.048	0.008	4.132	99.95	No
A5	首次完全充电 First cycle fully charged	49.227	4.133	49.223	0.008	4.131	99.95	No
A6	25次完全充电 25 cycles fully charged	49.042	4.142	49.039	0.006	4.139	99.93	No
A7	25次完全充电 25 cycles fully charged	48.893	4.143	48.888	0.010	4.141	99.95	No
A8	25次完全充电 25 cycles fully charged	49.001	4.139	48.997	0.008	4.137	99.95	No
A9	25次完全充电 25 cycles fully charged	49.282	4.141	49.279	0.006	4.138	99.93	No
A10	25次完全充电 25 cycles fully charged	49.043	4.140	49.038	0.010	4.137	99.93	No
以下空白 Blank below								

T.4: 冲击

T.4: Shock

样品编号 Sample No.	样品状态 Sample Status	测试前 Pre-test		测试后 After-test				有无泄漏、排气、 解体、破裂、起火 Leakage, Venting, Disassembly, Rupture, Fire(Yes/No)
		质量 Mass	开路电压 OCV	质量 Mass	质量损失 Mass Loss	开路电压 OCV	剩余电压 Residual	
		m ₁ (g)	V ₁ (V)	m ₂ (g)	(%)	V ₂ (V)	OCV (%)	
A1	首次完全充电 First cycle fully charged	49.202	4.132	49.199	0.006	4.130	99.95	No
A2	首次完全充电 First cycle fully charged	48.894	4.131	48.890	0.008	4.129	99.95	No
A3	首次完全充电 First cycle fully charged	49.189	4.129	49.185	0.008	4.126	99.93	No
A4	首次完全充电 First cycle fully charged	49.048	4.132	49.046	0.004	4.128	99.90	No
A5	首次完全充电 First cycle fully charged	49.223	4.131	49.223	0.000	4.129	99.95	No
A6	25 次完全充电 25 cycles fully charged	49.039	4.139	49.220	-0.369	4.137	99.95	No
A7	25 次完全充电 25 cycles fully charged	48.888	4.141	48.886	0.004	4.138	99.93	No
A8	25 次完全充电 25 cycles fully charged	48.997	4.137	48.993	0.008	4.134	99.93	No
A9	25 次完全充电 25 cycles fully charged	49.279	4.138	49.274	0.010	4.136	99.95	No
A10	25 次完全充电 25 cycles fully charged	49.038	4.137	49.035	0.006	4.135	99.95	No

以下空白

Blank below

T.5: 外部短路

T.5: External Short Circuit

样品编号 Sample No	样品状态 Sample Status	样品表面最高温度(°C) Highest External Temperature/°C	有无解体、破裂、起火 Disassembly, Rupture, Fire(Yes/No)
A1	首次完全充电 First cycle fully charged	59.5	No
A2	首次完全充电 First cycle fully charged	58.6	No
A3	首次完全充电 First cycle fully charged	58.3	No
A4	首次完全充电 First cycle fully charged	59.7	No
A5	首次完全充电 First cycle fully charged	60.1	No
A6	25 次完全充电 25 cycles fully charged	59.3	No
A7	25 次完全充电 25 cycles fully charged	58.8	No
A8	25 次完全充电 25 cycles fully charged	58.9	No
A9	25 次完全充电 25 cycles fully charged	59.2	No
A10	25 次完全充电 25 cycles fully charged	59.6	No
以下空白 Blank below			

T.6: 撞击**T.6: Impact**

样品编号 Sample No.	样品状态 Sample Status	样品表面最高温度(°C) Highest External Temperature/°C	有无解体、起火 Disassembly, Fire(Yes/No)
B1	首次 50%容量 First cycle charged 50% rated capacity	121.8	No
B2	首次 50%容量 First cycle charged 50% rated capacity	127.3	No
B3	首次 50%容量 First cycle charged 50% rated capacity	124.2	No
B4	首次 50%容量 First cycle charged 50% rated capacity	128.5	No
B5	首次 50%容量 First cycle charged 50% rated capacity	119.8	No
B6	25 次 50%容量 25 cycles charged 50% rated capacity	132.4	No
B7	25 次 50%容量 25 cycles charged 50% rated capacity	126.9	No
B8	25 次 50%容量 25 cycles charged 50% rated capacity	136.1	No
B9	25 次 50%容量 25 cycles charged 50% rated capacity	129.8	No
B10	25 次 50%容量 25 cycles charged 50% rated capacity	135.0	No
以下空白 Blank below			

T.7: 过度充电
T.7: Overcharge

样品编号 Sample No.	样品状态 Sample Status	有无解体、起火 Disassembly, Fire(Yes/No)
C1	首次完全充电 First cycle fully charged	No
C2	首次完全充电 First cycle fully charged	No
C3	首次完全充电 First cycle fully charged	No
C4	首次完全充电 First cycle fully charged	No
C5	25 次完全充电 25 cycles fully charged	No
C6	25 次完全充电 25 cycles fully charged	No
C7	25 次完全充电 25 cycles fully charged	No
C8	25 次完全充电 25 cycles fully charged	No
以下空白 Blank below		

T.8: 强制放电

T.8: Forced Discharge

样品编号 Sample No.	样品状态 Sample Status	有无解体、起火 Disassembly, Fire(Yes/No)
D1	首次完全放电 First cycle fully discharged	No
D2	首次完全放电 First cycle fully discharged	No
D3	首次完全放电 First cycle fully discharged	No
D4	首次完全放电 First cycle fully discharged	No
D5	首次完全放电 First cycle fully discharged	No
D6	首次完全放电 First cycle fully discharged	No
D7	首次完全放电 First cycle fully discharged	No
D8	首次完全放电 First cycle fully discharged	No
D9	首次完全放电 First cycle fully discharged	No
D10	首次完全放电 First cycle fully discharged	No
D11	25次完全放电 25 cycles fully discharged	No
D12	25次完全放电 25 cycles fully discharged	No
D13	25次完全放电 25 cycles fully discharged	No
D14	25次完全放电 25 cycles fully discharged	No
D15	25次完全放电 25 cycles fully discharged	No
D16	25次完全放电 25 cycles fully discharged	No
D17	25次完全放电 25 cycles fully discharged	No
D18	25次完全放电 25 cycles fully discharged	No
D19	25次完全放电 25 cycles fully discharged	No
D20	25次完全放电 25 cycles fully discharged	No
以下空白 Blank below		



UN38.3 测试报告

UN38.3 Test Report



电芯照片/Cell pictures



电池照片/Battery pictures



保护装置/Protective devices



* End of the report *