





中国认可 国际互认 检测 TESTING CNAS L0095

Page 1 of 14 Pages

Ref. No.: RZUN2018-2565

# 检测报告 TEST REPORT

**UN38.3** 

NAME OF SAMPLE: 产品名称:	Lithium Manganese Dioxide Battery
) 阳石你:	
CLIENT:	Titanium Innovations
委托单位:	-
CLASSIFICATION OF TEST:	Commission Test
检测类别:	委托测试



# 检测报告

#### **TEST REPORT**

Ref. No.: RZUN2018-2565

Pages

Page 2 of 14

Name of samples: Lithium Manganese Dioxide Battery 样品名称: -	Type/Model: 型号规格: CR9V 9,0V 1200mAh
Color: Orange/Black	Physical shape: Square
样品颜色:橙/黑	样品形状: 方形
Commissioned by: Titanium Innovations	Manufacturer: Titanium Innovations
委托单位: -	生产单位: -
Commissioner address: 50 School House Road Unit 2,	Manufacturer address: 50 School House Road
Old Saybrook CT 06475, USA	Unit 2, Old Saybrook CT 06475, USA
委托单位地址: -	生产单位地址: -
Classification of test: Commission Test	Quantity of sample: 8 battery packs, 20 Cells
检测类别: 委托测试	样品数量: 8 个电池组, 20 个电芯
Tested according to:	Sample identification:
测试标准: ST/SG/AC.10/11/Rev.6/Amend.1/Section 38.3	样品标识序号:b1#~b8#, c1#~c20#
Receiving date: 接样日期: 2018-09-07	Means of receiving: Submitted by Commissioner 接样方式: 委托单位送样
Completing date:	Test item: 7 items
完成日期: 2018-10-08	测试项目: 7 项

#### Test conclusion:

检测结论:

The Lithium Manganese Dioxide batteries submitted by Titanium Innovations are tested according to Section 38.3 of the Sixth revised Edition Amendment 1 of the Recommendations on the Transport of Dangerous Goods, Manual of Test and Criteria (ST/SG/AC.10/11/Rev.6/Amend.1/Section 38.3). The test items are full items. The test results comply with the relevant requirements of the standard.

由 Titanium Innovations 送检的 Lithium Manganese Dioxide patteries,依据《关于危险货物运输的建议书》试验和标准手册第六修订版修正 1 第 38.3 节进分检测、试验为全项目,测试结果符合标准相关要求。

CV企业检测专用章

签发日期:2018.10.08

Title:Manager批准人职务:经理

Approved by: Reviewed by:

Tested by:

批准:

■ 审核:

Zhang Siyan 检测:

Wei Gushua

Ref. No.: RZUN2018-2565 Page 3 of 14 Pages

Description and illustration of the sample:

样品说明及描述:

The sample's status is good

样品状况良好。

Test item	Sample No.	State	Remark
测试项目	样品编号	状态	备注
T.1~T.5	b1#~b4#	in undischarged states 未放电状态	-
1.1~1.5	b5#~b8#	in fully discharged states 完全放电状态	-
T.6	c1#~c5#	in undischarged states 未放电状态	-
1.0	c6#~c10#	in fully discharged states 完全放电状态	-
T.8	c11#~c20#	in fully discharged states 完全放电状态	-

Description of the sampling procedur	re:
--------------------------------------	-----

取样程序的说明:

/

Description of the deviation from the standard, if any:

测试结果不符合标准项的说明:

/

Remarks:

备注:

Throughout this report a comma is used as the decimal separator.

本报告中以逗号代替小数点。

Ref. No.: RZUN2018-2565 Page 4 of 14 Pages

## Photos of Samples and Labels/样品照片及标识

### Battery/电池 (CR9V 9,0V 1200mAh)











## Photos of Samples and Labels/样品照片及标识

Cell/电芯(CF502540 3,0V 1200mAh)





Ref. No.: RZUN2018-2565 Page 6 of 14 Pages

	ST/SG/AC.10/11/Rev.6/Amend.1/Section 38.3							
Clause	Requirements	Result	Verdict					
章节	标准要求	测试结果	判定					
38.3.4	Procedure/测试步骤		_					
	Test 1: Altitude simulation/测试 1: 高度模拟							
38.3.4.1	Test cells and batteries shall be stored at a pressure of 11,6 six hour at ambient temperature (20±5℃)/ 将电芯和电池在温力为不大于 11,6kpa 的环境中贮存不少于 6 个小时							
	Requirement/标准要求:	The samples						
	1 Cells and batteries Mass loss limit: ≤0,2% /样品质量损失≤0,2%	b1#~b8# : No leakage, no						
	2 Open circuit voltage not less than 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states.	venting, no disassembly, no rupture and no fire/编号为 b1#~b8#的样	Р					
	样品试验后开路电压应不低于试验前开路电压的 90%,此要求不适用于完全放完电的电池和电芯。 3 No leakage, no venting, no disassembly, no rupture and	品: 无漏液、无排气、无解体、无破裂						
	no fire 样品(电池)应无漏液、无排气、无解体、无破裂以及无着火现象的发生	以及无着火现象 The data see table1/数据见表 1						
	Test 2: Thermal test/测试 2: 热冲击							
	Test cells and batteries are to be stored for/电池存储条件如下:							
	1 one temperature cycle: 72±2℃(6h) —-40±2℃(6h) /一次温度循环为 72±2℃(6h) —-40±2℃(6h)							
	2 The maximum time interval between test temperature extremes is 30 minutes/温度转换最大间隔时间为 30min							
	3 This procedure is to be repeated 10 times/重复 10 次循环							
	4 after which all test cells and batteries are to be stored for 24 hours at ambient temperature (20±5℃)/循环结束后,电池在 20±5℃的条件下 搁置 24 小时.							
38.3.4.2	Requirements/标准要求	The samples b1#~b8#:	Р					
	1 Cells and batteries Mass loss limit: ≤0,2% /样品质量损失 ≤0,2%	No leakage, no						
	2 Open circuit voltage not less than 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states.	venting, no disassembly, no rupture and no fire/						
	样品试验后开路电压应不低于试验前开路电压的 90%,此要求不适用于完全放完电的电池和电芯。 3 No leakage, no venting, no disassembly, no rupture and no fire	编号为 b1#~b8#的样品: 无漏液、无排气、无解体、无破裂以及无着火现象						
	样品(电池)应无漏液、无排气、无解体、无破裂以及无着 火现象的发生	The data see table1/数据见表 1						

Ref. No.: RZUN2018-2565 Page 7 of 14 Pages

	ST/SG/AC.10/11/Rev.6/Amend.1/Section 38.3									
Clause	Requirements Result									
章节	标准要求	测试结果	判定							
	Test 3: Vibration/测试 3: 振动									
	1 Cells and batteries are firmly secured to the platform of the vibration machine /电 芯和电池牢固地安装在振动台(的台面)上									
	2 The vibration :a sinusoidal waveform with a logarithmic sweep between 7 Hz and 200 Hz and back to 7 Hz traversed in 15 minutes/振动以正弦波形式,以 7Hz 增加至 200Hz,然后在减少回到 7Hz 为一个循环,一个循环持续 15 分钟的对数前移传送。									
	3 the logarithmic frequency sweep is as follows: from 7 Hz a peak acceleration of 1 $g_n$ is maintained until 18 Hz is reached, The amplitude is then maintained at 0,8 mm (1,6 mm total excursion) and the frequency increased until a peak acceleration of 8 $g_n$ occurs (approximately 50Hz), A peak acceleration of 8 $g_n$ is then maintained until the frequency is increased to 200 Hz/对数扫频为:从 7 赫兹开始保持 1 $g_n$ 的最大加速度直到频率为 18 赫兹,然后将振幅保持在 0,8 毫米(总偏移 1,6 毫米)并增加频率直到最大加速度达到 8 $g_n$ (频率约为 50 赫兹),将最大加速度保持在 8 $g_n$ 直到频率增加到 200 赫兹。									
38.3.4.3	4This cycle repeated 12 times for a total of 3 hours for each of three mutually perpendicular mounting position of the cell. One of the directions of vibration must be perpendicular to the terminal face. /以振动的其中一个方向必须是垂直样品极性,对每个电芯从三个互相垂直的方向上循环 12 次,每个方向 3 个小时,共 9 小时。									
	Requirements/标准要求	The samples								
	1 Cells and batteries Mass loss limit: ≤0,2% /样品质量损失≤0,2%	b1#~b8#:  No leakage, no venting, no								
	2 Open circuit voltage not less than 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states.	disassembly, no rupture and no fire/ 编号为 b1#~b8#的样								
	样品试验后开路电压应不低于试验前开路电压的 90%,此要求不适用于完全放完电的电池和电芯。 3 No leakage, no venting, no disassembly, no rupture and	品: 无漏液、无排气、无解体、无破裂								
	no fire 样品(电池)应无漏液、无排气、无解体、无破裂以及无着 火现象的发生	3 No leakage, no venting, no disassembly, no rupture and no fire 样品(电池)应无漏液、无排气、无解体、无破裂以及无着 The data see								

Test 4: Shock/Test 4: 冲击
Test 4: Shock/Test 4: 冲击  1 Test cells and batteries shall be secured to the testing machine/以稳固的托架固定住每个电芯和电池样品的全部配件表面。  2 Each cell shall be subjected to a half-sine shock of peak acceleration of 150 g <sub>n</sub> and pulse duration of 6 milliseconds. Large cells may be subjected to a half-sine shock of peak acceleration of 50 g <sub>n</sub> and pulse duration of 11 milliseconds. / 对每个电芯以峰值为 150g <sub>n</sub> 的半正弦的加速度撞击,脉冲持续 6 毫秒,大型电芯须经受最大加速度 50g <sub>n</sub> 和脉冲持续时间 11 毫秒的半正弦波冲击。  Small batteries shall be subjected to a half-sine shock of peak acceleration of 150 g <sub>n</sub> (or Acceleration(g <sub>n</sub> )= $\sqrt{\frac{100850}{mass}}$ , which is smaller) and pulse duration of 6 milliseconds, large batteries shall be subjected to a half-sine of peak acceleration of 50 g <sub>n</sub> (or Acceleration(g <sub>n</sub> )= $\sqrt{\frac{30000}{mass}}$ , which is smaller) and pulse duration of 11 milliseconds/对每个电池以峰值为 150g <sub>n</sub> (或与 $\sqrt{\frac{100850}{mass}}$ 中的较小值)的半正弦的加速度撞击,脉冲持续 6 毫秒,大型电池须经受最大加速度 50g <sub>n</sub> (或与 $\sqrt{\frac{30000}{mass}}$ 中的较小值)和脉冲持续时间 11 毫秒的半正弦波冲击。  38.3.4.4  38.3.4.4
1 Test cells and batteries shall be secured to the testing machine/以稳固的托架固定住每个电芯和电池样品的全部配件表面。 2 Each cell shall be subjected to a half-sine shock of peak acceleration of 150 g <sub>n</sub> and pulse duration of 6 milliseconds. Large cells may be subjected to a half-sine shock of peak acceleration of 50 gn and pulse duration of 11 milliseconds. / 对每个电芯以峰值为 150g <sub>n</sub> 的半正弦的加速度撞击,脉冲持续 6 毫秒,大型电芯须经受最大加速度 50g <sub>n</sub> 和脉冲持续时间 11 毫秒的半正弦波冲击。  Small batteries shall be subjected to a half-sine shock of peak acceleration of 150 g <sub>n</sub> (or Acceleration(g <sub>n</sub> )= $\sqrt{\frac{100850}{mass}}$ , which is smaller) and pulse duration of 6 milliseconds, large batteries shall be subjected to a half-sine of peak acceleration of 50 g <sub>n</sub> (or Acceleration(g <sub>n</sub> )= $\sqrt{\frac{30000}{mass}}$ , which is smaller) and pulse duration of 11 milliseconds/对每个电池以峰值为 150g <sub>n</sub> (或与 $\sqrt{\frac{100850}{mass}}$ 中的较小值)的半正弦的加速度撞击,脉冲持续 6 毫秒,大型电池须经受最大加速度 50g <sub>n</sub> (或与 $\sqrt{\frac{30000}{mass}}$ 中的较小值)和脉冲持续时间 11 毫秒的半正弦波冲击。  38.3.4.4  38.3.4.4
冲击,总共经受 18 次冲击。  Requirements/标准要求: 1 Cells and batteries Mass loss limit: ≤0,2% /样品质量损失 ≤0,2% 2 Open circuit voltage not less than 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states.  样品试验后开路电压应不低于试验前开路电压的 90%,此要求不适用于完全放完电的电池和电芯。 3 No leakage, no venting, no disassembly, no rupture and no fire 样品(电池)应无漏液、无排气、无解体、无破裂以及无着 峰值加速度=150gn

Ref. No.: RZUN2018-2565 Page 9 of 14 Pages

	ST/SG/AC.10/11/Rev.6/Amend.1/Section 38.3							
Clause	Requirements	Result	Verdict					
章节	标准要求	测试结果	判定					
	Test 5: External Short Circuit/测试 5 外接短路							
	1 The cell or battery to be tested shall be temperature stabilized so that its							
38.3.4.5	external case temperature reaches 57±4℃/保持试验环境温度稳定在 57±4℃,以							
	使电芯或电池样品外表温度达到 57±4℃							
	2 the cell or battery shall be subjected to a short circuit	condition with a total						
	external resistance of less than 0,1 ohm at 57±4°C, This short circuit condition is							
	continued for at least one hour after the cell or battery external case temperature							
	has returned to 57±4°C, or in the case of the large batteries, has decreased by							
	half of the maximum temperature increase observed during the test and remains							
	below that value. /将样品正负极用小于 $0,1\Omega$ 的总电阻回路进行短路,样品的外表							
	温度恢复到 57±4℃之后保持短路状态 1 小时以上;对于大电池,电池温度降低至							
	最高温升值的一半时实验结束。							
	3 the cell or battery must be observed for a further six hour for the test to be							
	concluded,							
	/对电芯或电池必须进一步观察 6 个小时才能下结论。							
	Requirements/标准要求: During the test and within six hours after test ,the cells or	The samples b1#~b8# :						
	batteries 在测试过程中以及之后 6 个小时内,电芯或电池样品	no disassembly, no						
	1. External temperature not exceed 170℃	rupture and no fire/ 编号为 b1#~b8#的样						
	外表温度不超过 170℃	品: 无解体、无破裂						
	2. No disassembly, no rupture and no fire.	以及无着火现象 The data see						
	无解体、无破裂和无着火现象发生。	table1/数据见表 1						

1101. 110 112	RZUN2018-2565 Page 10 of ST/SG/AC.10/11/Rev.6/Amend.1/Section 38.3							
Clause	Requirements Result							
章节								
	Test 6: Impact / Crush / 测试 6: 撞击/挤压	VA W CPA	判定 P					
	Impact (applicable to cylindrical cells not less than 18mm in diameter) / 撞击(适用于直径不小于 18毫米的圆柱形电池)  1 This test sample cell or component cell is to be placed on a flat smooth surface/将试验样品用的电芯或聚合物电芯放在一个平坦光滑的平面上  2 A 15,8 mm diameter bar is to be placed across the center of the sample, A 9,1kg mass is to be dropped from a height of 61±2,5cm onto the sample./将一直径为15,8mm 的横木横过电池中部放置后,将一质量为9,1kg 的物体从61±2,5cm 的高度落向样品。  3 The test sample is to be impacted with its longitudinal axis parallel to the flat surface and perpendicular to the longitudinal axis of the 15,8 mm ± 0,1mm							
	surface and perpendicular to the longitudinal axis of the 15,8 mm ± 0,1mm diameter curved surface lying across the centre of the test sample. Each sample is to be subjected to only a single impact./ 接受撞击的试样,纵轴应与平坦的表面平行并与横放在试样中心的直径 15,8±0,1 毫米弯曲表面的纵轴垂直。每一个试样只经受一次撞击。							
	Requirements/标准要求: 1 Cells external temperature not exceed 170℃.电芯或电池的最高表面温度应不超过 170℃ 2 No disassembly, no fire within six hours of this test 试验结束后 6 个小时之内,电芯和聚合物电芯应无解体和无着火现象发生							
38.3.4.6	Crush (applicable to prismatic, pouch, coin/button cells and cylindrical cells less than 18mm in diameter) / 挤压(适用于棱柱形、袋装、硬币/纽扣电池和直径小于 18 毫米的圆柱形电池)  1 A cell or component cell is to be crushed between two flat surfaces. The crushing is to be gradual with a speed of approximately 1,5 cm/s at the first point of contact. The crushing is to be continued until the first of the three options below is reached. / 将电池或元件电池放在两个平面之间挤压,挤压力度逐渐加大,在第一个接触点上的速度大约为 1,5 厘米/秒。挤压持续进行,直到出现以下三种情况之一: (a) The applied force reaches 13 kN ± 0,78 kN. / 施加的力达到 13 千牛±0,78 千牛(b) The voltage of the cell drops by at least 100 mV,/电池的电压下降至少 100 毫伏(c) The cell is deformed by 50% or more of its original thickness./电池变形达原始厚度的 50%以上。  2. A prismatic or pouch cell shall be crushed by applying the force to the widest side. A button/coin cell shall be crushed by applying the force on its flat surfaces. For cylindrical cells, the crush force shall be applied perpendicular to the longitudinal axis. /棱柱形或袋装电池应从最宽的一面施压。纽扣/硬币形电池应从其平坦表面施压。圆柱形应从与纵轴垂直的方向施压。  Requirements/标准要求:  1 Cells external temperature not exceed 170℃.电芯或电池的最高表面温度应不超过 170℃ 2 No disassembly, no fire within six hours of this test 试验结束后 6 个小时之内,电芯和聚合物电芯应无解体和无着火现象 The data see							

	ST/SG/AC.10/11/Rev.6/Amend.1/Section	38.3					
Clause	Requirements	Result	Verdict				
章节	标准要求	测试结果	判定				
38.3.4.7	Test 7: Overcharge/测试 7: 过充电  1 The charge current shall be twice the manufacturer's recommended maximum continuous charge current/以 2 倍制造厂推荐的最大持续充电电流对样品充电  2 The minimum voltage of the test shall be as follows/本测试最小电压为:						
	a) When the manufacturer's recommended charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of the battery or 22V/ 如果厂家推荐的充电电压不超过 18V, 本测试的最小充电电压应是厂家标定最大充电电压的两倍或者是 22V 之中的较小者。						
	b) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1,2 times the maximum charge voltage/ 如果厂家推荐的充电电压超过 18V,本测试的最小充电电压应是厂家标定最大充电电压的 1,2 倍。						
	3 Tests are to be conducted at ambient temperature 20±5℃, The duration of the test shall be 24 hours/20±5℃ 的环境温度下,试验持续 24 小时。						
	Requirements/标准要求:						
	No disassembly and no fire within seven days of this test						
	试验样品在试验中和试验后 <b>7</b> 天内,应无解体和无着火现象 发生。						
	Test 8: Forced discharge/测试 8: 强制放电						
	Each cell shall be forced discharged at ambient temperature by connecting it in series with a 12 V D.C. power supply at an initial current equal to the maximum discharge current specified by the manufacturer,						
	20±5℃的环境温度下,将单个电芯连接在 12V 的直流电源上进行强制放电,此直流电源提供给每个电芯初始电流为制造厂指定的最大放电电流。						
	The specified discharge current is to be obtained by connecting a resistive load of the appropriate size and rating in series with the test cell. Each cell shall be forced discharged for a time interval (in hours) equal to its rated capacity divided by the initial test current (in ampere)						
38.3.4.8	指定的放电电流通过串联在测试电芯上的合适大小和功率的负载来获得,每个电芯的强制放电时间(小时)为额定容量除以初始电流(安培)。						
	Requirements/标准要求:	The samples					
	No disassembly and no fire within seven days of this test 试验样品在试验中和试验后 7 天内,应无解体和无着火现象发生。  This campos c11#~c20#: For voltage data before test, see table 3. / 试验前电压见表 3						
		No disassembly and no fire / 无解体、无着火现象					

Ref. No.: RZUN2018-2565 Page 12 of 14 Pages

	Table1: T1~T5 / 表 1. 试验 1~试验 5										
Sampl e No. 样品号	Mass prior to test / 试 验前质量	OCV prior to test /试 验前电	Test 1: / simula 测试 1: 词	ation/	Test 2: The 测试 2:		Test 3: V 测试 3		Test 4: 测试 4		Test 5: External Short Circuit/测试 5 外接短路
11 888 3	(g)	压(V)	Mass loss(%) 质量损失(%)	Change ratio 电压比(%)	Mass loss(%) 质量损失(%)	Change ratio 电压比(%)	Mass loss(%) 质量损失(%)	Change ratio 电压比(%)	Mass loss(%) 质量损失(%)	Change ratio 电压比(%)	Temp. (℃) 温度 (℃)
b1#	39,450	9,457	0,002	99,98	0,027	99,99	0,002	99,98	0,000	99,99	64,7
b2#	39,449	9,447	0,002	99,98	0,035	99,97	0,000	99,98	0,002	100,00	63,1
b3#	39,474	9,455	0,005	99,98	0,038	99,98	0,002	99,98	0,002	99,98	62,9
b4#	40,016	9,444	0,004	99,98	0,027	99,97	0,002	99,98	0,002	99,98	65,3
b5#	39,556	-	0,002	-	0,037	-	0,000	-	0,005	-	63,7
b6#	39,400	-	0,005	-	0,043	-	0,002	-	0,005	-	66,2
b7#	39,627	-	0,005	-	0,040	-	0,002	-	0,005	-	66,7
b8#	39,201	-	0,002	-	0,035	-	0,005	-	0,005	-	65,3

Ref. No.: RZUN2018-2565 Page 13 of 14 Pages

		Table2: Crush   表 2:挤压										
Test 6:	Sample No. 样品号	c1#	c2#	c3#	c4#	c5#	c6#	c7#	c8#	c9#	c10#	
Crush   测 试 6:挤压	OCV prior to test / 试验前电压(V)	3,148	3,152	3,148	3,157	3,155	2,600	2,633	2,611	2,634	2,611	
	Temp. (℃) 温度 (℃)	30,6	29,5	29,4	29,7	30,2	29,9	29,7	30,5	30,4	29,1	

Table 3: Forced discharge / 表 3. 强制放电											
Test 8: Forced discharge / 测试 8: 强 制放电	Sample No. 样品号	c11#	c12#	c13#	c14#	c15#	c16#	c17#	c18#	c19#	c20#
	OCV prior to test / 试验前电压(V)	2,600	2,633	2,611	2,627	2,633	2,631	2,627	2,625	2,621	2,609

# 注意事项 Important

1. 报告无检测单位印章无效。

The test report is invalid without the official stamp of CVC.

- 2. 未经本试验室书面同意,不得部分地复制本报告。
  - Nobody is allowed to photocopy or partly photocopy this test report without written permission of CVC.
- 3. 本报告无批准人、审核人及检测人签名无效。

The test report is invalid without the signatures of Ratifier, Reviewer and Testing engineer.

4. 本报告涂改无效。

The test report is invalid if altered,

5. 对检测报告若有异议,应于收到报告之日起十五天内向检测单位提出。

Objections to the test report must be submitted to CVC within 15 days.

6. 本报告仅对送检样品负责。

The test report is valid for the tested samples only.

7. 判定栏中"-"表示"不需要判定", "P"表示"通过", "F"表示"不通过", "N/A"表示"不适用"。

As for the Verdict, "-" means "no need for judgement", "P" means "pass", "F" means "fail" and "N/A" means "not applicable".

地 址:中国广州市科学城开泰大道天泰一路3号

Address: No.3, Tiantaiyi Road, Kaitai Avenue, Science City, Guangzhou P. R. China.

电 话(Tel): 020 32293888 传 真(FAX): 020 32293889 邮政编码(Post Code): 510663

E-mail: office@cvc.org.cn

http://www.cvc.org.cn